

AMENDMENTS TO THE CLAIMS:

The listing of claims will replace all prior versions, and listings of claims in the application:

LISTING OF CLAIMS:

1. (Currently Amended) A method of forming a lamp comprising:
providing a reflective interior surface comprising:
providing a layer of a reflective material, and
providing a protective layer which protects the ~~silver~~ layer of
reflective material against oxidation and sulfide formation; and
forming the lamp from the interior surface and a light source, ~~the~~ a thickness of
the protective layer being selected such that at least one of the following is satisfied:
 - (a) a color correction temperature of the lamp is no ~~less~~ more than 40K
~~below~~ less than a color correction temperature of the light source, and
 - (b) a % reflectance of the reflective interior surface is no ~~less~~ more than
about 3% ~~below~~ less than that of an equivalent reflective interior
surface without the protective layer in a visible spectral range of 400-
800 nm.
2. (Original) The method of claim 1, wherein both (a) and (b) are satisfied.
3. (Currently Amended) The method of claim 1, wherein the color correction
temperature is no ~~less~~ more than about 20K ~~below~~ less than that of the light source.
4. (Currently Amended) ~~The~~ A method of ~~claim 3, wherein the~~ forming a
lamp comprising:
providing a reflective interior surface comprising:
providing a layer of a reflective material, and
providing a protective layer which protects the layer of reflective
material against oxidation and sulfide formation; and
forming the lamp from the interior surface and a light source, a thickness of the
protective layer being selected such that a color correction temperature of the lamp is
greater than ~~the~~ a color correction temperature of the light source.

5. (Currently Amended) The method of claim 3, wherein the % reflectance of the reflective interior surface is at least 94.5% ~~layer~~ in the visible spectral range of 400-800 nm.

6. (Currently Amended) The method of claim 1, wherein the % reflectance of the reflective interior surface is no ~~less~~ more than about 2.5% ~~below~~ less than that of the layer of a reflective material in the visible spectral range of 400-800 nm.

7. (Original) The method of claim 6, wherein the layer of a reflective material has an average % reflectance of at least 90% in the visible range of the spectrum.

8. (Currently Amended) The method of claim 1, wherein the layer of reflective material comprises silver.

9. (Original) The method of claim 1, wherein the protective layer comprises at least one of the group consisting of:

oxides, suboxides, carbonated compounds and hydrogenated compounds of one or more of silicon, titanium, tantalum, zirconium, hafnium, niobium, aluminum, scandium, antimony, indium, and yttrium;

fluorides of one or more of magnesium, sodium, aluminum, yttrium, calcium, hafnium, lanthanum, ytterbium, and neodymium;

nitrides of one or more of silicon, aluminum, chromium, and titanium; and
zinc sulfide.

10. (Original) The method of claim 9, wherein the protective layer includes at least one of an oxide of tantalum and an oxide of silicon.

11. (Original) The method of claim 10, wherein the protective layer comprises silica and has a thickness in one of the following ranges:

50-200 Å;

850-1400 Å; and

2600-3250 Å.

12. (Currently Amended) ~~The~~ A method of ~~claim 1, wherein~~ forming a lamp comprising:

providing a reflective interior surface comprising:

providing a layer of a reflective material, and

providing a protective layer which protects the layer of reflective material against oxidation and sulfide formation; and

forming the lamp from the interior surface and a light source, the protective layer ~~has~~ having an optical thickness t_{OPT} which satisfies the relationship:

$$1.1(1 + 0.9n) \leq t_{OPT} \leq 1.4(1 + 0.9n)$$

where n is an integer from 0 to 5;

whereby at least one of the following is satisfied:

(a) a color correction temperature of the lamp is no more than 40K less than a color correction temperature of the light source, and

(b) a % reflectance of the reflective interior surface is no more than about 3% less than that of an equivalent reflective interior surface without the protective layer in a visible spectral range of 400-800 nm.

13. (Original) The method of claim 1, wherein the method further includes a tubulation step, the step of providing a reflective layer including:
forming the reflective layer after the tubulation step.

14. (Original) The method of claim 1, wherein providing the protective layer includes depositing the layer by chemical vapor deposition on a housing.

15. (Cancelled)

16. (Cancelled).

17. (Cancelled).

18. (Cancelled).

19. (Cancelled).

20. (Currently Amended) A method of forming a lamp comprising:
providing a reflective surface which includes silver;

determining an oscillating function when one of color correction temperature and percent reflectance is plotted against optical thickness for a lamp formed from the reflective surface and a protective layer;

covering the reflective surface with a protective layer which is light transmissive, ~~the protective layer exhibiting an oscillating function when one of color correction temperature and percent reflectance is plotted against optical thickness for a lamp formed from the reflective surface and protective layer,~~ the optical thickness of the protective layer being selected, based on said oscillating function, such that the following relationships are satisfied:

the color correction temperature is no ~~less~~ more than about 20K ~~below~~ less than that corresponding to a protective layer optical thickness of zero; and

the reflectance is no ~~less~~ more than 3% ~~below~~ less than that corresponding to an optical thickness of zero in the visible range of the spectrum.

21. (New) The method of claim 1, wherein at least (a) is satisfied.

22. (New) The method of claim 1, wherein the reflective layer comprises silver, the color correction temperature is no more than about 20K less than that corresponding to a protective layer optical thickness of zero and the reflectance is no more than 3% less than that corresponding to an optical thickness of zero in the visible range of the spectrum.

23. (New) A lamp formed by the method of claim 1.

24. (New) A lamp formed by the method of claim 4.

25. (New) A lamp formed by the method of claim 12.